APRIL 2014

ZAR DECK AND SIDING CLEAR WOOD SEALER & NATURAL TONER BASE TINTING FORMULATION

MATCHING: ZAR DECK AND SIDING CLEAR WOOD SEALER AND NATURALTONER COLORS

SYSTEM: PPG USING 48 INCREMENTS PER FLUID OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

B - Lamp Black

C - Yellow Oxide

D - Thalo Green

E - Thalo Blue

F- Red Iron Oxide

G - Durable Yellow

L - Raw Umber

M – Durable Red

W – Titanium White

CLEAR WOOD SEALER & NATURAL TONER COLORS - PPG

AUTUMN CHESTNUT TONER 766

NATURAL TONER BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
C – Yellow Ox.	0	2	C – Yellow Ox.	0	8	C – Yellow Ox.	0	40
L – Raw Umber	0	4	L – Raw Umber	0	16	L – Raw Umber	1	32
M – Durable Red	0	0.5	M – Durable Red	0	2	M – Durable Red	0	10

GOLDEN WHEAT TONER 764

NATURAL TONER BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
C – Yellow Ox.	0	6	C – Yellow Ox.	0	24	C – Yellow Ox.	2	24
L – Raw Umber	0	3.5	L – Raw Umber	0	14	L – Raw Umber	1	22
M – Durable Red	0	1.75	M – Durable Red	0	7	M – Durable Red	0	35

NATURAL HONEY TONER 759

NATURAL TONER BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
C – Yellow Ox.	0	10	C – Yellow Ox.	0	40	C – Yellow Ox.	4	8

NATURAL REDWOOD TONER 761

NATURAL TONER BASE

Quart Formula			Gallon Formula			Five Gallon Formula			
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s	
C – Yellow Ox.	0	6	C – Yellow Ox.	0	24	C – Yellow Ox.	2	24	
F – Red Iron Ox.	0	1.5	F – Red Iron Ox.	0	6	F – Red Iron Ox.	0	30	
L – Raw Umber	0	0.5	L – Raw Umber	0	2	L – Raw Umber	0	10	

ROASTED ALMOND TONER 767

NATURAL TONER BASE

Quart Formula			Gallon Formula			Five Gallon Formula			
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s	
B – Lamp Black	0	3	B – Lamp Black	0	12	B – Lamp Black	1	12	
C – Yellow Ox.	0	5	C – Yellow Ox.	0	20	C – Yellow Ox.	2	4	
F – Red Iron Ox.	0	1	F – Red Iron Ox.	0	4	F – Red Iron Ox.	0	20	